



Re-Pulpability Testing

Embossed Cups - Leetha

07/02/2020

Ed Perry
Kemsley Technical Department



Testing

Sample



Full disintegration



Handsheet, post full disintegration



Comments

- **Fibre dispersion** – Good, fully dispersed fibre after standard disintegration
- **Flake content** – Good, Less than 5%
- **Sheet Ash content** – Very good, Less than 1% (test performed on standard sample material)
- **Dirt Content** – Average, Handsheets contain a fair amount of glue and white flake

Test Results	
Flake %	1.12%
Usable Fibre %	98.88%
Sheet Ash %	0.57%



Thank You

Danke Dankjewel Благодаря 谢谢 Hvala Dík Tak Aitäh Kiitos Merci Ευχαριστώ
Köszönöm Grazie Paldies Ačiū Ви благодарам شکرالکم Dziękuję Obrigado Mulțumesc
Ďakujem Gracias Tack ขอบคุณ Teşekkür ederim

The Power of Less®